



**Eurobandas**  
The Granite Tile Company

**ROSAVEL**

## Technical specifications

Petrographic denomination	Boitite granite with megacrysts	UNE-EN 12407
Apparent density	2620 Kg/m <sup>3</sup>	UNE-EN 1936
Open porosity	0.9 %	UNE-EN 1936
Water absorption	0.3 %	UNE-EN 13755
Abrasion resistance	17.5 mm.	UNE-EN 14157
Breaking load at dowel hole	3000 N.	UNE-EN 13364
Compressive strenght	108 MPa	UNE-EN 1926
Flexural strenght	7.8 MPa	UNE-EN 12372
Frost resistance (Decrease of Rf after 48 cycles)	10.1 %	UNE-EN 12371
Slip resistance	Polished: 57/16 SRV	UNE-EN 14231
	Honed: 78/46 SRV	

