



Eurobandas
The Granite Tile Company


BLUE PEARL

Blue Pearl



Technical specifications

Petrographic denomination	Monzonite	UNE-EN 12407
Apparent density	2730 Kg/m ³	UNE-EN 1936
Open porosity	0.1 %	UNE-EN 1936
Water absorption	0.04 %	UNE-EN 13755
Abrasion resistance	16.0 mm.	UNE-EN 14157
Breaking load at dowel hole	3700 N.	UNE-EN 13364
Compressive strenght	231 MPa	UNE-EN 1926
Flexural strenght	14.8 MPa	UNE-EN 12372
Rupture energy, thickness 30 mm	2.7 j	UNE-EN 14158
Slip resistance	Honed: 49/6 SRV	UNE-EN 14231



EUROBANDAS S.A.

Magdalena, s/n, Ribadelouro
36710 Tui (Pontevedra) España
Tlf: +34 986 639 600 / Fax: +34 986 639 633
E-mail: eurobandas@eurobandas.com
Web: www.eurobandas.com